

Amendments to the Claims:

This listing of claims will replace all prior versions and listings of claims in the application:

Listing of Claims:

1. (currently amended) A non-aqueous electrolyte secondary cell comprising:
a cathode comprising $\text{Li}_x\text{Fe}_y\text{PO}_4$ $\text{Li}_x\text{M}_y\text{PO}_4$ having an olivine structure and having a particle diameter not greater than ~~10~~ 1 micrometers and wherein $0 < x \leq 2$ and $1 \leq y \leq 2$;
an anode wherein said anode comprises sintered carbon material prepared by sintering a carbon material capable of doping/dedoping lithium; and
a non-aqueous electrolyte solution.
- 2-3. (canceled)
4. (currently amended) A non-aqueous electrolyte secondary cell comprising:
a cathode having a molded body comprising a cathode active material and a conductive agent, said active material comprising $\text{Li}_x\text{Fe}_y\text{PO}_4$ $\text{Li}_x\text{M}_y\text{PO}_4$ having an olivine structure and having a particle diameter not greater than ~~10~~ 1 micrometers wherein $0 < x \leq 2$ and $1 \leq y \leq 2$;
an anode having a molded body comprising a material selected from the group consisting of an anode active material capable of doping/dedoping lithium, a conductive agent, and mixtures thereof; and
a non-aqueous electrolyte solution.
- 5-13. (canceled)
14. (previously presented) The non-aqueous electrolyte secondary cell of Claim 1, wherein said carbon material is selected from the group consisting of non-graphitizable carbon, graphitizable carbon, graphite, and mixtures thereof.

15. (previously presented) The non-aqueous electrolyte secondary cell of Claim 1, wherein said non-aqueous electrolyte solution comprises an electrolyte salt and a non-aqueous solvent.

16. (previously presented) The non-aqueous electrolyte secondary cell of Claim 15, wherein said electrolyte salt is a lithium salt having ion conductivity.

17. (previously presented) The non-aqueous electrolyte secondary cell of Claim 16, wherein said lithium salt is selected from the group consisting of LiClO_4 , LiAsF_6 , LiPF_6 , LiBF_4 , $\text{LiB}(\text{C}_6\text{H}_5)_4$, LiCl , LiBr , $\text{CH}_3\text{SO}_3\text{Li}$, $\text{N}(\text{C}_n\text{F}_{2n}\text{SO}_2)_2\text{Li}$, and mixtures thereof.

18. (previously presented) The non-aqueous electrolyte secondary cell of Claim 15, wherein said non-aqueous solvent is selected from the group consisting of propylene carbonate, ethylene carbonate, 1,2-dimethoxyethane, 1,2-diethoxyethane, diethyl carbonate, methyl ethyl carbonate, dimethyl carbonate, γ -butyrolactone, tetrahydrofuran, 1,3-dioxolane, 4-methyl-1,3-dioxolane, diethyl ether, sulfolane, methyl sulfolane, acetonitrile, propionitrile, and mixtures thereof.

19. (previously presented) The non-aqueous electrolyte secondary cell of Claim 4, wherein said anode active material comprises a carbon material selected from the group consisting of non-graphitizable carbon, graphitizable carbon, graphite, and mixtures thereof.

20-21. (canceled)

22. (previously presented) The non-aqueous electrolyte secondary cell of Claim 4, wherein said anode conductive agent is selected from the group consisting of SiB_4 , SiB_6 , Mg_2Si , Ni_2Si , TiSi_2 , MoSi_2 , CoSi_2 , NiSi_2 , CaSi_2 , CrSi_2 , Cu_5Si , FeSi_2 , MnSi_2 , NbSi_2 , TaSi_2 , VSi , WSi_2 , ZnSi_2 and mixtures thereof.

23. (previously presented) The non-aqueous electrolyte secondary cell of Claim 4, wherein said non-aqueous electrolyte solution comprises an electrolyte salt and a non-aqueous solvent.

24. (previously presented) The non-aqueous electrolyte secondary cell of Claim 23, wherein said electrolyte salt is a lithium salt having ion conductivity.

25. (previously presented) The non-aqueous electrolyte secondary cell of Claim 24, wherein said lithium salt is selected from the group consisting of LiClO_4 , LiAsF_6 , LiPF_6 , LiBF_4 , $\text{LiB}(\text{C}_6\text{H}_5)_4$, LiCl , LiBr , $\text{CH}_3\text{SO}_3\text{Li}$, $\text{N}(\text{C}_n\text{F}_{2n}\text{SO}_2)_2\text{Li}$, and mixtures thereof.

26. (previously presented) The non-aqueous electrolyte secondary cell of Claim 23, wherein said non-aqueous solvent is selected from the group consisting of propylene carbonate, ethylene carbonate, 1,2-dimethoxyethane, 1,2-diethoxyethane, diethyl carbonate, methyl ethyl carbonate, dimethyl carbonate, γ -butyrolactone, tetrahydrofuran, 1,3-dioxolane, 4-methyl-1,3-dioxolane, diethyl ether, sulfolane, methyl sulfolane, acetonitrile, propionitrile, and mixtures thereof.